

Geofoam No. 5008

Subject: Chemical Exposure

Date: February 2011 (Revised January 2019)

ThermaFoam R-Control Geofoam is used in a wide variety of applications. There may be instances in applications where the ThermaFoam R-Control Geofoam is subjected to chemical exposure. This can be by either direct exposure to the chemicals or to their chemical vapors. Exposure to chemicals most commonly occurs during the installation process or as the result of a contaminated site conditions after the ThermaFoam R-Control Geofoam is in place.

The attached table provides general guidance for the resistance of ThermaFoam R-Control Geofoam to a number of chemicals. The table is intended to provide a preliminary guide, but does not guarantee long term performance of ThermaFoam R-Control Geofoam when in contact with the listed or any other chemicals.

It is recommended that laboratory tests modeled to represent chemical exposure in end use conditions be conducted to assure efficacy of the ThermaFoam R-Control Geofoam.

When the exposure of ThermaFoam R-Control Geofoam to any harmful chemicals is a possibility or in doubt, the protection of ThermaFoam R-Control Geofoam by means of an appropriate barrier material is required.

Rating: Overall chemical exposure performance is noted by a rating symbol.


S = Satisfactory M = Marginal *U = Unsatisfactory

| Chemical | Rating |
|--------------------------|--------|
| Acetic Acid (5%) | S |
| Acetic Acid (10%) | M |
| Acetone | U |
| Ammonia | S |
| Benzene | U |
| Butly Alcohol | S |
| Citric Acid (10%) | S |
| Citric Acid (20%) | M |
| Detergents | M |
| Diesel Fuel | U |
| Ethyl Acetate (98%) | U |
| Ethyl Alcohol (95%) | M |
| Ethylene Glycol | S |
| Gasoline | U |
| Hexane | U |
| Hydrochloric Acid (10%) | S |
| Hydrochloric Acid (38%) | M |
| Hydrochloric Acid (100%) | U |
| Hydrogen Peroxide (30%) | S |
| Isopropyl Alcohol | M |

| Chemical | Rating |
|-----------------------------|--------|
| Kerosene | U |
| Methyl Alcohol | M |
| Methyl Ethyl Ketone | U |
| Mineral Oil | S |
| Motor Oil | M |
| Nitric Acid (20%) | U |
| Paint Thinner | U |
| Petroleum Jelly | S |
| Potassium Hydroxide (%30) | S |
| Propyl Alcohol | M |
| Propylene Glycol | S |
| Sodium Chloride (saturated) | M |
| Sodium Hypochlorite (15%) | S |
| Sodium Hydroxide (40%) | S |
| Sulphuric Acid (50%) | S |
| Sulphuric Acid (96%) | S |
| Toluene | U |
| Turpentine | U |
| Water (salt/sea) | S |
| Xylene | U |

* ThermaFoam R-Control Geofoam must be protected by an appropriate barrier material if there is a potential of exposure to these chemicals.

This information contained herein is provided for general purposes only. By providing this information, your ThermaFoam makes no guaranty or warranty, and does not assume any liability with respect to the accuracy or completeness of such information, and hereby expressly disclaims any implied warranties of fitness of the use of ThermaFoam R-Control Geofoam for a particular purpose.



www.thermafoam.com



1240 Hwy 77
Hillsboro, TX 76645

Office: 254-582-2730
Fax: 254-582-2811