

Molded Polystyrene Insulation.

ThermaFoam R-Control molded polystyrene insulation is a cost effective, durable, and energy efficient solution for all types of insulation applications. ThermaFoam R-Control Insulation is an insulation manufactured to provide architects, specifiers, distributors, and contractors all the features and benefits inherent in a quality insulation.

R-value - ThermaFoam R-Control 130 has an R-value that never changes over time.

Strength - ThermaFoam R-Control 130 has a compressive strength of 13 psi.

Moisture Resistance - ThermaFoam R-Control 130 is a closed cell polystyrene insulation and is resistant to moisture gain.

Vapor Permeable - ThermaFoam R-Control 130 allows moisture vapor to move through its structure.

Drying Potential - ThermaFoam R-Control 130 rapidly releases absorbed moisture.

Applications.


- Cavity Wall
- Wall Sheathing
- Precast Concrete Core
- Flat/Tapered Roofing
- Plaza Deck/Vegetative Green Roof
- Drainage Board
- Waterproofing Protection

Proven to meet, or exceed, building codes.

ThermaFoam R-Control insulation is manufactured under an industry leading quality control program monitored by UL and further recognized in UL Evaluation Report UL ER40338-01.



ThermaFoam R-Control insulation meets Type VIII of ASTM C578, "Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation".



www.thermafoam.com

THERMAFOAM R-CONTROL		130	
Compressive Strength ^{1,2} @ 10% deformation, min. ASTM D1621		psi (kPa)	13 (90)
R-value ¹ , Thermal Resistance, per inch, ASTM C518	25°F	°F·ft ² ·h/Btu (°K·m ² /W)	4.5 (0.80)
	40°F	°F·ft ² ·h/Btu (°K·m ² /W)	4.3 (0.76)
	75°F	°F·ft ² ·h/Btu (°K·m ² /W)	3.9 (0.69)
k-value Thermal Conductivity ASTM C518	25°F	Btu·in/°F·ft ² ·h (W/°K·m)	0.22 (0.032)
	40°F	Btu·in/°F·ft ² ·h (W/°K·m)	0.24 (0.034)
	75°F	Btu·in/°F·ft ² ·h (W/°K·m)	0.26 (0.037)
Density, min., ASTM C303		lb/ft ³ (kg/m ³)	1.15 (18)
Flexural Strength ¹ , min. ASTM C203		psi (kPa)	30 (208)
Water Vapor Permeance ¹ of 1.0 in. thickness, max., perm ASTM E96			3.5
Water Absorption ³ , volume % ASTM C272			0.3
Flame Spread Index ASTM E84			<25
Smoke Developed Index ASTM E84			<450
Maximum long-term use temperature			165°F (74°C)
ASTM C578 Compliance, Type			VIII

¹ Please refer to ASTM C578 specification for complete information.

² Compressive strength is measured at 10 percent in accordance with ASTM C578. A safety factor is required to prevent long-term creep for sustained loads. For static loads, a safety factor of 3:1 is recommended.

³ ASTM C272 24 hour immersion followed by 24 hour storage in 75°F/50%RH air.